

Aman

Er. Iswor Rawat

Engineer

Construction Materials

The different materials used in construction industry such as stones, bricks, cement, aggregate, lime, mortar, timber, steel, paint, Varnish, plastics, glass etc... & other insulating materials are called Construction materials.

Stone

The stone are derived from rocks which from the earth crust & have no definite shape or size. → Natural Material

→ Crushing strength of good building stone not less than 100 kg/cm²

→ Crushing strength of building stone Always 1000 kg/cm²

Stone	Heavy stone	Light stone	Soft stone
Suitable	Retaining Wall	Masonry Wall	Ornamental Works

→ Study of rock, their properties & origin — Petrology

Classification of Rocks / stones

A Based on formation / Geological Classification

① **Igneous Rock** Igneous rocks are formed by the solidification of molten mass of silicates below or at the surface of earth. Which formed by cooling of magma.

→ main constituent — Silica

Types of Igneous Rock

① **Intrusive Rock** If the cooling of magma below the surface of earth. Two Types

② **Plutonic Rock** Depth (3-8 km) eg, granite, pegmatite etc

③ **Hypabyssal Rock** Depth (2-3 km) eg, dolerite, diorite.

Note Book

Date : 20 / /

Aman

⑥ **Extrusive Rock** if the **cooling of magma at the surface of earth**
→ also **Volcanic Rock** - eg; basalt, trap, obsidian, pumice, dacite etc.

Example of Igneous Rock : syenite, gabbro.

② **Sedimentary Rock** sedimentary rocks are formed by the **gradual deposition of materials** like debris, sand, silt, clay etc.

→ **main constituent** debris, gravel, sand, silt, clay etc.

→ It is also known as **aqueous rock**. → process of formation - **petrified**

→ These are also **stratified** because these rocks are **formed in layers**

→ **Example** : lime stone, sand stone, gypsum, dolomite, chalk, shale, kankar, conglomerate stone, tripoli, diatomite, chert etc.

③ **Metamorphic Rock** Metamorphic rocks are formed by the **change in texture or mineral composition or both of igneous or sedimentary rock due to high temperature & heavy pressure.**

→ **main constituent** : Igneous & sedimentary rock.

→ **Example** : Marble, gneiss, quartzite, slate, schist, serpentine

Igneous or sedimentary Rock	Metamorphic Rock
Granite	Gneiss
Sand stone	Quartzite
Shale	Slate & schist
Lime stone & dolomite	Marble
Conglomerate	Gneiss, schist etc.

⑧ Physical classification

① **Stratified Rock** The stratified rocks are those which gives **distinct layer** which can be separated.

→ **Example** : all sedimentary rocks, marble, quartzite.

Aman

② **Unstratified Rock** The unstratified rocks are those which do not show any sign of strata & can not be easily split into slab.

Example: All igneous rocks.

③ **Foliated Rock** The foliated rock having tendency to split in a certain direction.

Example: All metamorphic rock except marble & quartzite.

C Chemical classification

Rock	main constituent	Example
① Argillaceous	Clay or alumina	Slate, laterite, kaoline
② Silicious	Silica	Granite, gneiss, basalt, trap, syenite, sand stone, quartzite
③ Calcareous	Lime or Calcium oxide (CaO)	Limestone, marble, dolomite

Characteristics of good building stone

- ① Appearance & Colour
- ② Weight
- ③ Water absorption < 5% Rejected > 10%.
- ④ Fire resistance
- ⑤ Electrical resistance
- ⑥ Hardness
- ⑦ Durability
- ⑧ Easy of working
- ⑨ Toughness
- ⑩ Soluble salt of 0%.
- ⑪ Sp. gravity $\rightarrow$ not less than 2.4
- ⑫ minimum crushing strength = 100 kg/cm²
- ⑬ Heaviness

Note stone ke strength wet condition me 30-40% kam hoga, dry condition me तुलनामा।

Test of stone

Test of stone	Used
Absorption test	To determine amount of water absorbed in 24 hrs.
Acid test	To check weather resistance.
Crushing test	To determine the strength of stone.
Hardness test	To determine hardness of stone.
Impact test	To determine the toughness of stone.
Smith test	To find dirty materials in stone.
Attrition test	To check resistance to abrasion.
Brard test	for frost resistance.
Microscopic test	Find out grain size, existing of pores etc.

Important Terms

Quarrying

→ The process of taking out stone from natural rock is known as quarrying. → open part of the natural rock from which useful materials is obtained is known as quarry.

→ During quarry of stone, moisture present in the stone, is called

quarry sap → The process of removing quarry sap from stone is called seasoning of stone. Which process complete = 6-12 months.

Tool for quarrying Pick axes (पिके), Crow bar (क्राउ बार), Jumper, wedge etc.

Method of Quarrying

① Digging or Excavation It carried out with the help of tool such as pick axes, crow bar, hammer, shovel (खुदो) etc. case soft stone

② Heating The top surface of rock is heated by placing wood with fuel on it. fire will be allowed for some hours. after heated which separates from the rock.

③ Wedging This method is applicable when the rock contains cracks

Note Book

Date : 20 / /

Aman

or joints on it. steel wedges or steel points are put in those cracks & hit them with hammer.

⊕ **Blasting**. In this method explosive are used to separate the stones from parent rock. **Case** Hard rock & without any crack. → The holes are drilled in the rock & explosives are arranged in the holes & blasted with proper safety.

Tool for Blasting Steel jumper of 1.8 - 3m long & 40mm diameter with chisel, tamping needle, scraping spoon etc.

Explosive Explosive used in blasting are gun powder, dynamite, guncotton, cordite etc. **Note** gun powder is not used for blasting under water. **most powerful** Gun cotton.

Dressing

It is the process of giving proper shape, size & finish. It is done either manually or mechanically.

Artificial stone made by cement & natural aggregate with required shape & size.

Tools used in dressing

- ① soft stone chisel ② crow chisel ③ punch chisel
- ④ Drafting chisel ⑤ Mason hammer ⑥ Fore hammer
- ⑦ Scrabbling hammer ⑧ Spalling hammer (for rough dressing)

Minerals in Rocks

A mineral may be defined as an organic substance, having usually a definite chemical composition, which can be expressed by a chemical formula & physical properties.

→ The properties of rocks are mainly dependent on the types of minerals present in rock.

Ex. Quartz, mica, calcite, alumina & felspar.

Note Book

Date : 20 / /

Amam

Properties of Minerals

- ① **Cleavage** Tendency of minerals to break with smooth flat surface
- ② **Texture** arrangement constituent minerals grains available in stone
- ③ **Lusture** shine surface of minerals. its appearance under reflect light
- ④ **colour** is the main characteristics of mineral.
- ⑤ **streak** colour of powder form of minerals.
- ⑥ **weathering** effect of atmospheric conditions

Moho's scales

→ It was created in 1812 by the German geologist & mineralogist Friedrich Moho. → used to determine hardness of stone.

Hardness	Minerals	Suitability of stone	
Moho's scale			
1 (softest stone)	Talc	Parts of structure	Stone
2	Gypsum	1. Building construction	Laterite
3	Calcite	2. cement concrete	Basalt & trap
4	Fluorite	3. Roof covering, flooring,	
5	Apatite	damp proofing, sill & window.	slate
6	Feldspar	4. Interior decoration of building	serpentine.
7	Quartz	5. Railing ballast	Granite, gneiss, trap
8	Topaz	6. for fire resistance	compact sand stone
9	Sapphire	7. Road metal	Granite & basalt
10 (Hardest stone)	Diamond	8. Bridge, pier, docks	Granite & gneiss
Flagstone		9. Ornamental work in building	Red & yellow type of basalt & trap.
		10. partitions in urinals & bathroom	slate
→ Sedimentary rock			
→ Form of sandstone			
composed of feldspar & quartz.			
→ Grain size = 0.15 - 2mm		11. Ornamental building, monument, statue & curved work	Marble
→ Use paving slabs, roofing, memorials etc.			

Some special stones properties

Stone	Type	Nature	Colour	Uses	road pavement
Granite	Igneous	Hard & strongest	Gray, green, brownish, black	Pier, bridge, abutment, light house	road pavement
Basalt, trap	"	Hard & heavy	Gray, bluish, black	Road metal, paving, concrete	-
Pumice	Igneous (foth)	Light	Gray, brownish	Light weight aggregate.	-
Lime stone	Sedimentary	Stratified	White, gray, yellow, black	-	-
Sand stone	"	" & soft	" "	Building element	-
Shale	"	Laminated, soft	-	-	-
Conglomerate	"	Granular	Light colour, black	-	-
Gneiss	Metamorphic	Hard	" "	Paving, road metal	-
Marble	"	Stratified	White, black & mixed	Ornamental work, statue	-
Slate	"	Laminated, hard	Gray, black, blue, purple	Roofing, dpc, flooring, bathrooms	-
Schist	"	Weak	Greenish, yellowish, brownish black	Ready used for structure	-
Magma	"	Hard	-	Pressing of metal road	-
Laterite	Argillaceous	Soft	Red, Yellow, brown, black	Light road, inferior type building	-

Answer

Availability of stones in Nepal

1. **Slate** Sindhupalchowk, Nuwakot, Dhading, Tanahun, Chitwan, Ramechhap, Sankhu
2. **Gravel** Lalitpur, Palpa.
3. **Talc** Sindhupalchowk, Makawanpur
4. **Sandstone** Kathmandu, Lalitpur, Kaski, Palpa, Dang
5. **Marble** Kathmandu, Lalitpur
6. **Berri** Taplejung, Sankhu sabha
7. **Granite** Sankhusabha, Nuwakot
8. **Turmalin** Sankhusabha, Nuwakot
9. **Limestone** Kathmandu (Ramkot), Dhankhuta (Thuliwa, Budhimorang), Chitwan (pile), Makawanpur (Nibuwatar), Tanahun (Dandakot)

Cement

cement can be defined as a materials with **adhesive & cohesive** (जोड्ने) properties which makes it capable of bonding materials fragments into a compact whole.

→ It provides good bond between two materials & provides good strength. → It obtained by mixing limestone & clay, burning them & grinding to fine powder.

→ **Popular cement** ordinary portland cement (most used)

→ **Specific gravity** = 3.15 → **Water absorption** = not more than 5%

→ **Density of cement** = 1440 kg/m³

Raw Materials of cement

Ingredients	Comp%	Function
Lime (CaO)	60-65	controls strength, sound, strong
		Excess Unsound, expand & disintegrate
Silica (SiO ₂)	17-25	Give strength Excess slow setting.
Alumina (Al ₂ O ₃)	3-8	Quick setting Excess lowers the strength.

Note Book

Date : 20 / /

Aman		
Iron Oxide (Fe_2O_3)	0.5-6	Give, hardness, strength & fusion. Excess
Magnesium Oxide (MgO)	0.5-4	Give colour & hardness. Excess → discolour
		Excess cracks in mortar & concrete.
Sulphur Trioxide (SiO_2)	1-2	Make sound Excess unsound
Alkalies	1.8	Small quantities Excess Efflorescence

* Besides, Gypsum ($CaSO_4$) — 2-4 % → control initial setting time

Bogue's compound / composition of cement clinker :

Compound	Comp %	Function
Alite (C_3S)	25-50	→ It generates more heat of hydration → Develops early strengths & hardness.
Belite (C_2S)	25-40	→ It generates less heat of hydration → Develops ultimate strength.
Celite (C_3A)		→ It react rapidly with water.
	5-11	→ It generates more heat of hydration → Help to setting of cement.
Felite (C_4AF)		→ Less cementing Value.
	8-14	→ React very slow → Increase Volume of cement. → Reduced cost.

All the above compounds undergo some chemical combination during the manufacturing process & from clinker. the constituents of the end product are called Bogue compound.

Note : → High % of Alite & low % of Belite in cement results.

① Rapid hardening. ② High early strength ③ High heat of generation. ④ Less resistance to chemical attack.

→ Low % of Alite & high % of Belite in cement results.

① Slow hardening ② High ultimate strength ③ Less heat of hydration ④ Greater resistance to chemical attack.

* % of Alite & Belite for portland cement = 70-80 %

Note Book

Date : 20 / /

Mixing of raw materials	Burning	Grinding
Ball mill	Rotary kiln	Tube mill

Types of Cement

① Ordinary portland cement (OPC) → **Properties** → sufficient resistance shrinkage & cracking. Less resistance chemical attack. → medium rate of development of strength & heat of hydration. **Uses** → General construction → Small structures.

② Portland pozzolana cement (PPC) pozzolana materials = 10-25%. **Properties** → Gain strength slower than OPC → Ultimate strength more than OPC → Less heat of hydration → Greater resistance chemical attack. **Uses** → Under construction of water → Sewage works → Suitable for small concrete works.

③ Rapid hardening portland cement (RHPC) **Properties** → Early strength greater than OPC. → Contain Lime more than OPC. heat of hydration Higher than OPC. → C_3S more than OPC. → 3 day strength of RHPC = 7 day strength of OPC → OPC **गुणवत्ता कम**. **Uses** → Emergency work, Road construction.

Not Use Mass concrete construction.

④ Extra rapid hardening cement **Properties** → obtained by Mixing $CaCl_2$ (2%) with RHC. **Uses** Road works.

⑤ Sulphate resisting cement (SRC) **Properties** → Manufactured by Grinding OPC clinker with gypsum. **Uses** Marine condition, basement foundation, Waste water treatment.

⑥ Super sulphate cement (SSC) **Properties** → Manufactured by 80-85% granulated slag, 10-15% burnt gypsum & 5% OPC clinker. → Highly resistance sulphate attack. **Uses** Marine work.

⑦ Low heat cement (LHC) **Properties** → C_3S & C_3A less & C_2S more. → Strength is gained at slow rate. → Ultimate strength same as OPC. **Uses** Mass concrete, dam, retaining wall, bridge, abutment.

Aman

⑧ Blast furnace cement **properties** → obtained by Mixing portland cement clinker, gypsum, granulated blast furnace slag. **Uses** Mass concrete due to low heat of hydration.

⑨ Quick setting cement **properties** → obtained by Adding Al_2SO_4 & $CaCl_2$ with opc → **Reduced** amount of gypsum. **Uses** Under water construction.

⑩ High alumina cement **properties** → Amount of alumina & calcareous materials are high → can withstand high temperature. **Uses** Refractory concretes.

⑪ Resistent cement **properties** → **Hardening time** = 8-10 min. **Uses** Very cold area/winter season.

⑫ Coloured cement **properties** → prepared by china clay & Chalk → **Amount of pigment** = 5-10%. **Cost** 2 times of opc. **Uses** Architectural purpose.

⑬ High strength cement **properties** → special type of opc → **compressive strength** higher than opc.

⑭ Hydrophobic cement **properties** obtained by mixing opc clinker with water repellent film from the substance like acetic acid, stearic acid etc.

⑮ Masonary cement

⑯ Oil Well cement

⑰ Expansive cement

Temperature at the time of testing = $25^{\circ}C - 29^{\circ}C$

Maximum % of pigment in colour of cement = 10%

The weight of magnesia should not be greater than 5%

Aman

Test of cement

① Fineness test

→ check proper grinding of cement & cementing value.

→ Method ① sieve method ② Air permeability method.

→ sedimentary residue of opc cement should not be greater than 10% of sample in Is sieve no 90micron

1mm = 1000 micron

② consistency test

→ Find the proper amount of water to be added to the cement.

→ performed by Vicat's apparatus Consists, plunger Diameter 10mm

Length = 40-50mm →

③ Soundness test

→ Find the presence of uncombined lime & magnesia in cement which causes the expansion of cement.

→ Done by Le-chatelier's apparatus.

→ According to Is, Expansion = not exceed 10mm, Portland cement

④ Setting time test

→ Done by Vicat's apparatus

Types of cement	Initial Setting time (min)	Final setting time (min)
Ordinary portland cement	30	600
Portland pozzolana cement	30	600
Rapid hardening cement	30	600
Sulphate resisting cement	30	600
Super sulphate cement	240 (4hr)	270 (4hr-30 min)
Low heat cement	60	600
Blast furnace cement	30	600
Quick setting cement	5	30
High alumina cement	30	600
White portland cement	30	600

Aman

⑤ Tensile strength test

- Tested by Briquette testing machine.
- Cement & sand ratio 1:3 (mortar)
- Average tensile strength after 3 day of curing = not less than 20 kg/cm^2 & 7 day = not less than 25 kg/cm^2 .

⑥ Compressive strength test

- Standard cube made of good portland cement & sand mortar in ratio 1:3 → Size of cube mould = 7.06 cm
- Done by compression testing machine
- Cubes should be kept at temperature $27^\circ \pm 2^\circ \text{C}$
- Compressive strength after 3 day = not less than 115 kg/cm^2 & 7 day = 175 kg/cm^2 → Three cubes are tested

⑦ Loss of ignition test

- Loss of weight of cement 1 gram of sample is heated at standard temperature → Loss of ignition = not exceed 4%.

Manufacture of cement

① Dry process

- Limestone & clay are ground separately to fine powders by a grinding mill & mixed together in desired proportions.
- Water (about 12%) is then added & the resulting product is dried & burnt in kilns.
- Clinker obtained after burning is added 3-5% of gypsum & ground to fine powder.
- This final product is cement.

② Wet process

- Limestone is ground separately.
- Clay materials are mixed with water in wash mills & stored.
- Now Crushed dry limestone & wet clay are mixed correct proportion.

Note Book

Date : 20 / /

Dry Process	Wet process
→ slow & costly. ..	→ quick & easy
→ size of the kiln needed to manufacture the cement is smaller.	→ Bigger
→ More economically.	→ Less economically.
→ Moisture contents of this pellets is 12%.	→ Moisture content of this slurry is 30-50%.
→ Amount of heat required is lower. so required lower fuel.	→ Amount of heat required is higher. so required higher fuel.
→ Steps	→ Steps
① Treatment of raw materials.	① collection of raw materials.
② Burning of dry mix.	② preparation slurry (crushing, grinding & mixing of raw materials)
③ Grinding of clinker.	③ Burning, ④ Grinding of clinker.
④ Packing & storage.	

Specific surface

Types of cement	OPC & PSC	PPC	LHPC	RHPC	SRPC
Specific surface area (cm^2/gm)	2250	3000	3200	3250	4000

Flash set It is the property of concrete by which upper surface of concrete becomes hard without setting the inner portion.
 → This effect is found due to the presence of tri-calcium aluminate (C_3A)

Setting & hardening of cement

→ The chemical reaction between cement & water is called **hydration of cement**. The phenomenon by virtue of which the plastic cement change into a solid mass is known as **setting of cement**.
 → The phenomenon by virtue of which the elements paste sets & develops setting is known as **hardening of cement**.

Aman

Strength of Cement

After Months	3	6	12	24
Strength reduced	20%	30%	40%	50%

Freshness of cement

- The Colour of cement is uniformly greenish grey.
- A handful of cement, thrown into a bucket of water, floats.
- Hand is thrust into a bag of cement, it feels cool & it feel smooth.

Specification of storage & transport of cement bag

Height of cement bag = 18 cm

Area of cement bag = 3000 cm^2 (40×75)

Space between pile = 1.6 m

space from wall = 30 cm (minimum)

Height from ground surface = 20 cm (minimum)

packing of bags = 50 kg per bag

No. of bag should not be more than 15 in horizontally & 10 in Vertically. → Wide $\nless 3 \text{ m}$ → Height $\nless 2.7 \text{ m}$

Transport With help of truck, lorry & tractor etc.

Admixtures

Added Less than 5%.

The admixtures are the materials other than the basic ingredients of cement concrete added to the concrete mix to improve certain properties, like strength, durability, workability.

→ The addition of admixture is done immediately before or during mixing. → Available both powder & aqueous solution.

Functions of Admixtures

- Improves workability, strength & durability.
- Increase bond strength betⁿ concrete & reinforcement.

Note Book

Date : 20 / /

Amam

- Improving the water proofing properties.
- Reduce shrinkage during setting of mortar.
- Reduce bleeding & segregation effects of concrete.
- To produce colour of concrete.
- To decrease weight of concrete.

Note Admixtures are added to Fresh & hardened concrete to add some special properties.

Types of Admixtures

- ① **Accelerator** → Added upto 2% by weight of cement.
→ Concrete set & hardened quickly. → Generally used in construction in cold climates → Reduce ultimate strength & initial setting time of concrete. → Examples Aluminium chloride, Sodium carbonate, Calcium chloride, Silicon fluoride etc.
- ② **Retarder** → Increase initial setting time & hardening time of concrete. → for long distance → Examples calcium sulphate (CaSO_4) gypsum, sugar, glucose, starch, cellulose → Added 2-3%.
- ③ **plasticizer** Also 'water reducing admixtures' → Added to concrete mix for making more plastic without any further addition of water. Added below 0.5% → Example salt of hydroxylated acids.
- ④ **Air-entering agent** Example Resins, fatty acids, oils, aluminium & zinc powdered etc.
- ⑤ **Bleeding agent** Example paraffin wax
- ⑥ **Colouring agent** Example Red oxide, ferrous oxides, Chromium oxide

Clay & Clay Products

Brick

Bricks are the small, solid structural unit of rectangular shape & convenient size made from suitable types of clay hardened by the heat or chemical action.

Brick	Stone
→ Lighter than stone	→ Heavier than brick.
→ Made of clay.	→ Obtained from rock.
→ Sp. gravity = 1.8	→ Sp. gravity = 2.6
→ Water absorption = less than 15%	→ Water absorption = less than 5%
→ Less durable than stone.	→ High durable than brick.
→ Uniform Colour & shape.	→ No uniform Colour & shape.
→ Absorbs lesser heat.	→ Absorbs more heat.
→ Overall cost of manufacture is less.	→ Overall cost of manufacture is high.

Brick Earth Brick earth is the mixture of clay & sand which when mixed with water becomes plastic & can be easily moulded. also dried without cracking & warping.

Ingredients of Brick Earth

Ingredients	Comp%	Function
Silica (SiO_2)	50-60	→ main ingredients. → Retain shape. → Imports durability → prevent shrinkage & warping. Excess Brittle & weak.
Alumina (Al_2O_3)	20-30	→ provides plasticity → Makes brick hard on drying. Excess Crack & warp
Lime (CaO)	< 10%	→ Reduce shrinkage Excess melt & lose its shape. Result Thoma brick, black colour
Iron Oxide (Fe_2O_3)	< 7%	→ Give red colour Excess dark blue colour, not present in the form of iron pyrite.
Magnesia (MgO)	< 1%	→ Reduce warping & shrinkage. Excess Yello Colour, decay
Alkalies	< 10%	→ for quick setting, Help to melt the brick. Excess efflorescence.

Harmful Ingredients	
Ingredients	Causes
Carbonaceous matter	Brick black
Iron Pyrite	Split the brick to pieces.
Organic matter	Brick porous
pebbles & gravels	Difficult to mix. Result non-homogenous brick
Sulphur	Brick discolour.
Water	Shrinkage during burning

Manufacture of Bricks/Preparation of Brick Earth

- ① Un-soiling** It is the process of removal of top layer of earth ($\approx 20\text{cm}$) to get the soil free from pebbles, gravel, roots etc.
- ② Digging** It is the process of excavation of soil by adding fly ash, sandy, loam, rice husk etc.
- ③ Weathering** It is the process of exposing the soil in open weather after mixing small amount of water to improve plasticity & strength.
- ④ Blending** It is the process of mixing the appropriate constituent of bricks such as sandy earth, Calcareous earth etc. Except water
- ⑤ Tampering** It is the process of kneading the soil either by feet of men or pugmill. $\rightarrow$ The operation of tampering with pug mill is known as pugging. $\rightarrow$ In tampering water & other substance are mixed together to improve plasticity & durability of bricks.
- ⑥ Moulding** It is the process of making the bricks of required shape & size from the tampered or pugged clay. $\rightarrow$ Moulding done by either hand or machine.
 - Hand: ① Ground ② Table
 - Machine: ① Plastic clay ② Dry clay
- ⑦ Drying** It is the process of remove the moisture to control the shrinkage, save fuel & time during drying.
 - $\rightarrow$ Natural drying $\rightarrow$ slow
 - $\rightarrow$ Artificial drying $\rightarrow$ Fast
 - $\rightarrow$ cost
- ⑧ Burning** Three stage
 - ① Dehydration ($400^\circ - 650^\circ\text{C}$)
 - ② Oxidation ($650^\circ - 1000^\circ\text{C}$)
 - ③ Vitrification ($900^\circ - 1100^\circ\text{C}$)

Answer

→ Kiln में burnt गरिष्ठो शब्द clamp का poor quality का brick को।

Types of kiln

→ **Pizza Wall !!**

- ① clamp or open kiln → Temporary structure
- ② Intermittent kiln → permanent structure → hot continuously
- ③ Continuous kiln → permanent structure → Burning Continuous

Types of continuous kiln

→ Low initial cost

→ chimney Ht. = 17m

→ semi/over ground

- ① Bull's trench kiln shape Elliptical Run Dry seasons only 60%
- ② Hoffmann's kiln shape Circular Run full year place over ground
- ③ Tunnel kiln → 80-90% → High initial cost → chimney Ht. = 30m

Note 20 tones coal are required for burning of 100000 bricks.

→ The amount of fuel required for burning of bricks is

0.075 - 0.1 T/m³ (coal) & 0.1 - 0.15 T/m³ (wood).

Classification of Bricks

A) On the basis of Field practice

① First class Brick

- They are well burnt & regular shape & size.
- Have uniform texture & colour. (deep red colour)
- Sufficiently hard & sound.
- Minimum crushing strength = 105 kg/cm². 10.5 N/mm²
- specific gravity = 1.8 → Metallic sound
- Water absorption capacity = not exceed 15% (for 24 hrs)
- Not break, dropped from height 1-2 m.
- Size of brick, NS = 230 x 115 x 57 mm.
- Used in masonry, flooring, facing works.

② Second class Brick

- They are well burnt but irregular shape & size
- Does not have uniform texture & colour.
- Not so hard. → Ringing sound

Amu

→ Minimum crushing strength = 70 kg/cm^2 7 N/mm^2

→ Water absorption capacity = $< 20\%$

→ Used in interior wall construction.

③ Third class Brick

→ They are under burnt & irregular shape & size.

→ Does not have uniform texture & Yellowish colour.

→ soft → dull sound

→ Minimum crushing strength = $35-70 \text{ kg/cm}^2$ 3.5 N/mm^2

→ Water absorption capacity = $< 25\%$ 7 N/mm^2

→ Used in interior & temporary structure.

④ Overburnt or Thama Brick

→ They are overburnt & irregular shape & size. → Brittle

→ Dark in colour. → produce metallic ringing sound.

→ Hard & strong → crushing strength = $> 15 \text{ N/mm}^2$

→ Used in aggregate for concrete, road metal, filling material

⑤ On the basis of use

① Common Brick Used for filling, backing

② Facing Brick Used in front of building wall. Good appearance

③ Engineering Brick Used → strong, impermeable, smooth & hard.

⑥ On the basis of finish

① Sand face brick (sand चर्को) ② Rustic brick (विभिन्न colour रङ्गमा)

⑦ On the basis of manufacture

① Handmade brick

② Machine made brick

⑧ On the basis of Burning

↓ clinkers brick

① Pale brick	② Body brick	③ Arch brick
Unburnt	Well burnt	Over-burnt

Aman

Testing of Brick

① Compressive strength test

- minimum no. of specimen = 5
- Specimen brick is immersed in water for 24 hours.
- Frog of brick is filled with 1:3 cement mortar & stored in damp jute bags for 24 hours.
- & then immersed in water for 3 days.
- specimen placed on compression testing machine.
- Load is applied at uniform rate of 14 N/mm^2 per minute.
- Maximum load is recorded. (specimen fails दुराकी)
- $$\text{Compressive strength} = \frac{\text{Maximum load at failure}}{\text{Loaded area of brick}}$$

② Water absorption test

- 3-5 samples of bricks are taken.
- It is done at a temperature of $27 \pm 2^\circ\text{C}$.
- The specimen brick is first weighted dry. ' W_1 '
- Then immersed in water for 24 hours.
- It is weighted again. ' W_2 '

$$\text{Water absorption} = \left(\frac{W_2 - W_1}{W_1} \right) \times 100$$



③ Efflorescence test → measure white patches

Efflorescence	Nil	Slight	Moderate	Heavy	Serious
deposits (white)	not found	< 10%	10-50%	> 50%	Exposed area

④ Warping test Check bend & twist of brick.

- Size Mortar = 10mm
- ⑤ Dimension test NS = 230mm x 115mm x 57mm
- IS = 19cm x 9cm x 9cm → 4cm

No. of brick	NS (1m ³)	① Hand made	— 560	530 IS
		② Machine Made	— 530	500

Defect of Bricks

- ① Under burning. brick **Absorbs** Water **Reduce** strength
- ② over burning. brick **produced** soften mass **Loose** shape
- ③ Chuff Hot brick **or** cool water **गर्हा**, **Crack** **or** **deformation** हुनु।
- ④ Black Core → Carbon **or** bituminous matter **चाही** oxidation द्वारा completely removed **जए**, **अर्थात** **improper burning** का कारण हुनु।
- ⑤ Cracks or checks → **Reason** Excess of Water & lumps of lime.
- ⑥ Efflorescence → brick **मा** **White** **or** **gray** salt deposition हुनु।
Reason Alkalies present in soil.
- ⑦ Bloating → **Brick swollen** (फुलेको). **Reason** Excess of Carbonaceous Matter & Sulphur.
- ⑧ Lamination → **Reason** Entrapped air in brick **Reduce** strength **Weak in structure**
- ⑨ Spots → Dark sulphur spots due to iron sulphides.

Some other Types of Bricks

Fire Bricks / Refractory Bricks

- It is made of **fire clay** at **high temperature** in a special kiln.
- **Crushing Strength** = 125 kg/cm^2 **Water absorption** = 5-10 %
- **Used** Combustion Chamber → **Chromic** Natural refractory brick.
- **Dolomite** & **Bauxite** Basic refractory brick. → **Unit Weight** = 2400 kg/m^3

Hollow Bricks

- Volume not less than half of the gross Volume.
- **Used** Non load bearing wall & ornamental works.

Other Important Terms

Terracotta → It is a type of **fired clay** or **earthenware**.

Made by mixing Clay with Water, **shaping**. → Burnt in special **Kiln** Nam

Muffle furnace **Temperature** $1100 - 1200^\circ\text{C}$. **Used** pottery, sculpture (मूर्तिकला), decorative objects, architectural features, building materials such as roof tiles, bricks etc.

Aman

Surkhi → Form of powdered brick. → Made by finely grinding, burnt clay bricks. → Mixed with cement to create Mortar. → Substitute for sand → Improve strength & durability of concrete & mortar. Reduce shrinkage & cracking.

Fly ash → fine, powdery substance → produce during the combustion of coal. → Used as a partial replacement for cement in concrete. Improve strength & durability. Also used in production of bricks, as a soil amendment & as a component in the production of lightweight aggregates.

Porcelain → Type of ceramic material → Made by heating materials, typically including clay in combination with other minerals, at high temperature. Properties: Hard, white, translucent (पारदर्शी) & glazed surface. → zero absorption. Used in dinnerware, vases (फूलदान), figurines (सूर्ति) & decorative.

Bricks Bond

→ pattern in which bricks are laid to form a wall or other structure.

Types of Bond	Explanation
Stretcher Bond	→ Bricks are laid as stretcher on the face of the wall. → Used for single brick wall or half brick wall. → Also used for cavity wall as less cutting required.
Header Bond	→ Bricks are laid as header on the face of the wall. → Used for one brick wall.
English Bond	→ Bricks are laid by alternate course of headers & stretchers. → Strongest bond & carry heavy load. → commonly used for all wall thickness.
Flemish Bond	→ Bricks are laid by each course alternate headers & stretchers. → More decorative.

Note Book

Date : 20 / /

Amam

Frog → **Depression** on the top of the brick. → **Works** as a key at time of laying of bricks. → **Size** 10cm x 4cm x (10-20)mm

Used Advertisement of manufacture & reduce weight.

Brick Nogging → **Construction techniques** → **Bricks are fill in a Wooden frame.** **Purpose** provide additional strength & stability to building. Wall or ceiling.

Quality of Good Brick

- ① **Shape & size** → Uniform in size, uniform surface with **Well defined edge**
- ② **Colour** → **Copper colour.**
- ③ **Structure** → **Fine Compact & uniform structure.**
- ④ **Hardness** → sufficiently hard & **not be scratched by fingernail.**
- ⑤ **Porosity** → **Not absorb too much water.**
- ⑥ **Strength** → sufficiently strong & not crack under loading.
- ⑦ **Durability** → Not damaged by the environment.
- ⑧ **Resistance to fire**
- ⑨ **Resistance to efflorescence**

Note : **Compressive strength** **Hand made brick** = 30-150 kg/cm²
Machine made brick = 4-50 kg/cm²

→ Normally, **Height of Chimney** = 30m

→ **Glazing** is used to make earthenware impervious.

→ **Damper** → **metal plate** → **Used** close or open chimney of kiln.

↳ **Purpose** Regulate the flow of air in the kiln during the firing process

→ **Internal size of mould** take slightly (about $\frac{1}{10}$ th) **greater than burnt brick**

→ **Height of wall** can be raised in one day, ① **Stone masonry** = 60cm.

② **Brick masonry** = 100cm.

→ **Wt of one brick** = 2-3 kg → **Volume of one brick** = 1680 cm³

→ **Density of common red brick** = 1620-1900 kg/m³

Aman

Paints & Varnishes

Paints & Varnishes are used to protect metals, timber or plastered surface from the corrosive effects of weather, heat, moisture or gases. They are also used to improve their appearance.

Paint

It is the fluid paste prepared by mixture of base with vehicle, pigments, thinner, drier, adulterants, extender etc.

Uses/Function of paint ① Decoration purpose ② conservation purpose ③ Hygienic purpose ④ prevents from corrosion.

Ingredients of paints

Ingredients	Functions
1. Base	→ Body of paint. → Also called Oxides of metal. → It gives a thin layer (film) which protects from weathering effect. → It has binding properties. → Example Used on Wooden surface - White lead, zinc white. Used on Metal surface - Red lead, Iron oxide. → Aluminium powder etc.
2. Vehicle	→ Also called carrier, liquid, drying oil. → It binds base & pigments together. → It spread the base over the surface. → Examples Linseed oil (mostly used), Fish oil, tung oil, nut oil, poppy oil etc.
3. Pigments	→ Gives colour to the paint. → < 10%. → White colour → White lead, zinc oxide → Red colour → Red lead, Iron oxide, Carmine, vermillion → Blue colour → Indigo, Cobalt oxide.

Note : Weather resistance in zinc white

Note Book

Date : 20 / /

Aman	
	→ Brown colour — Copper oxide, raw & burnt umber
	→ Green colour — Chromium oxide, Copper sulphate
	→ Black colour — Lamp black, Vegetable & Ivory black.
	→ Yellow colour — Yellow chrome, Ochre, raw sienna.
4. Drier	→ It helps to dry the vehicle. → < 8%.
	→ Example Letharge (mostly used), zinc sulphate, lead acetate, red lead, magnesium.
5. Thinner (solvent)	→ Also called Volatile substance (आँकड़ें उड़ने वाले)
	→ Make its application easy & smooth & thin.
	→ Examples Turpentine (mostly used), Petroleum, kerosene, spirit, naphtha, water etc.
6. Adulterants (inert filler)	→ Increase weight & durability. Reduce cost
	→ Examples Silica, Aluminium, silicate, magnesium silicate, calcium carbonate, Barium sulphate, etc.
7. Extender	→ Increase Volume Examples Silica, talc, gypsum

Note more poisonous — **Lead paint**

Types of paint

Types of paint	Uses
① Aluminium paint	→ Resist High temperature. → Uses oil & gas storage tank, hot water pipes, electrical & telephone poles, silos, metal roof etc.
② Asbestos paint,	→ Fire resistance → prevents leakages. Uses metal roof, gutter, outer surface of basement wall
③ Bronze paint	→ High reflective Used radiator of vehicles.
④ Enamel paint	→ Used Timber, concrete, metal etc.
⑤ Cellulose paint	→ Used in expensive materials. → Ducco paint → Used Air-plane, ships, car etc.
⑥ oil paint.	→ Ordinary paint, easily available, cheap. → Used Automobiles.

Amam

⑦ Emulsion paint	Used concrete surface in wet area.
⑧ Fluorescent paint	→ It has shining property. → Visible at night.
⑨ Cement paint	Base white cement Thinner water → Used concrete face, plastered surface.
⑩ Plastic paint	→ Dense in nature → Give very attractive looks. Used Auditorium, Showrooms, office etc.
⑪ Bitumen paint	→ It gives highly protective layer. → Used Under water pipes.
⑫ Casein paint	→ Used plastered surface, Wall & Ceiling etc.
⑬ Zinc paint	→ Used Illumination of maps.

Preparation of paints

Stone pestle

- ① First of all, base is finely ground with the help of muller & then mixed with vehicle. It gives thick paste.
- ② Then, this thick paste is mixed with thinner. It gives a consistent / thin paste.
- ③ Now, separately ground pigment & driers.
- ④ Then, all above three paste are mixed & give a paint.

Defects in paint

- ① Blistering → swelling of paint Reason अन्तिम coat मा oil के मात्र ज्यादा हुआ या paint surface मा air फंसेका कारण। peeling → case of moisture
- ② Chalking → Conservation of paint into powder form Reason paint मा oil को मात्रा कम हुआ।
- ③ Checking → Formation of cracks on surface of paint (हल्का) → Reason paint मा tensile strength कम हुआ। र paint चिसो मिसममा apply गर्दा। crazing → cracks small area मा produced हुने।
- ④ Crocodiling → cracks large area मा produced हुने।
- ⑤ Cracking → Cracks developed throughout the thickness of paint. Reason paint मा drier ज्यादा हुआ।

Amara

- ⑤ Alligatoring → one layer of paint slide over the another.
→ Reason Hard paint is applied over a soft one or vice versa.
- ⑥ Flaking → Detachment of paint film from the surface.
- ⑦ Discoloration → Alteration in the original colour.
(Ex:)

Varnish

It is a homogenous mixture of natural or synthetic resin with solvent & drier. → Varnish dries off & leaves a transparent or semi-transparent film of resin. → It does not contain pigments.

Function of Varnish ① protects the painted surface ② Gives shining effect to the painted surface. ③ Gives brilliancy to the wooden surface, photograph, map etc

Ingredient of Varnish

Resin → Principle constituent → Examples Copal, amber, gum, mastic
Solvent → Examples Linseed oil, turpentine oil, methylated spirit or alcohol
Drier → Examples Lead acetate, White Copper, Letharge.

Types of Varnish

Types of Varnish	Explanation
① Oil Varnish	→ Resin + Linseed oil + Turpentine + drier → Dries off very slow. → Most durable. → Used Exterior & Interior surface. → Example Copal Varnish.
② spirit Varnish	→ Resin + Methylated spirit → Brilliant appearance → Dries off very quickly → Less durable. → Used Interior surface. → Eg. French polish, Lacque
③ Flat Varnish	→ Give dull appearance. → Used Timber for protection.

Aman	
④ Spar Varnish	→ Sticky in nature as temperature rise → Used spars, Exterior part of ship, boat
⑤ Water Varnish	→ Hot water + ammonium etc. → Used photograph, map.
⑥ Turpentine Varnish	→ Dries off quickly → Less durable than oil Varnish Used Metal painted surface → Not so tough.
⑦ Asphalt Varnish.	Used Fabricated steel Works.

Distempers → Also called Water paint → obtained by
Mixing White chalk & water. Base chalk Thinner Water
Main principle constituents: chalk. Removed by water
→ Less durable Use Temporary & Interior surface.
→ Not exposed to atmosphere. → for colour used to pigments

Bitumen

It is a binding material, which is in solid or semi-solid state.

Properties of Bitumen:

Colour Black State semi-solid sp. gravity 1.09 soluble in
Carbon disulphide, Carbon tetrachloride, Chloroform, benzene,
→ Non-crystalline solid → Viscous material → gets softer
as temperature rise. → Catch fire at 200°C → Ductile in
nature. → Chemical Compound Carbon & hydrogen
Derived from petroleum crude oil (फज्ज्या तेल)
→ Bitumen is not affected by air, light or water individually
but in combination they can make in brittle & porous.

Aman

Uses of Bitumen

- Road pavement → Paint formation → Crack repairs
- Heat insulation purpose → DPC, leakage prevention → Batteries
- Roof sealing → Joint filler, etc.

Classification of Bitumen

1 General Classification

(a) Cutback Bitumen → Obtained by Bitumen + solvent (Kerosene, petroleum, naphtha, gasoline etc) → Solvent turns the bitumen from semi-solid to liquid state. → No heat is needed before using it.

→ Used Road pavement in cold area, Manufacturing of paint, Soil stabilization. Mountainous area. stabilizing agent 1-1.

(b) Bitumen Emulsion → Obtained by Bitumen + water + Emulsifier
→ It is an aqueous solution (पानी मिलाई रखने) → Used Road pavement, Soil stabilization.

(c) Blown or Oxidised Bitumen → Obtained by passing air at high temperature & pressure. Function Heat insulation Used flooring, Roofing, Joint etc.

(d) Plastic Bitumen → Obtained by Bitumen + Inert filler (40-45%)
→ Inert filler Asbestos powder. → Used Crack repairs Boiling Point 150°C

(e) Rut or straight run Bitumen → Obtained by after distilling a crude oil having required penetration, viscosity. → Used without further treatment.

2 Based on source ① Natural Bitumen ② petroleum Bitumen.

3 Based on consistency (at 18°C)

① Solid Bitumen ② semi-solid Bitumen ③ Liquid Bitumen

4 Based on Application (Uses)

① Road Construction Bitumen ② Building Bitumen ③ Roofing Bitumen

Aman

Test of Bitumen

Types of Test	Explanation
① Penetration Test	Equipment: penetrometer
	Measure: softness or hardness of bitumen.
Note: Actual penetration	Expressed $\frac{1}{10}$ th of mm
Value (30-40) mm,	Needle allowed penetrates Time = 5 sec
$30 \times \frac{1}{10} - 40 \times \frac{1}{10}$ mm	Standard Temperature: 25°C
3 mm - 4 mm Hard	→ penetration value: $\frac{30}{40}, \frac{80}{100}$ etc.
(80-100) mm,	In 30/40 → 30 = lower penetration limit
8 mm - 10 mm Soft	→ 40 = Higher " "
② Softening point test	Equipment: Ball & Ring
	Measure: softening point.
Temperature	Temperature increase rate: 5°C/min
Susceptibility	→ Measured temperature Ball drops from Ring.
	→ For good bitumen softening point = 35°C - 70°C
③ Ductility Test	Equipment: standard briquette testing Machine.
	Measure: elongation, before failure
at 27°C	→ pulling rate: 50 mm/min
	→ Measured distance: Bitumen break.
	→ For good bitumen ductile value = 50 cm
④ Specific Gravity	Equipment: pycnometer
	Measure: specific gravity.
at 27°C	→ sp. gravity = 1.03, (0.97 - 1.02) Highway
⑤ Viscosity Test	Equipment: orifice viscometer
	Measure: Resistance to flow
	→ Measure in term of time (sec).
	→ size of orifice = 4 mm, 10 mm

Note Book

Date : 20 / /

Amam	
⑥ Flash & Fire point test	Equipment Pensky. martens Tester Measure Flash & Fire point. → Generally, Value = 200°C
⑦ Loss of Ignition Test	Equipment Hot air oven, perforated metal shelf, container, thermometer, weighing balance. → Measure Loss of Weight → $\neq 1\%$
⑧ Solubility Test	→ Soluble in Carbon disulphide, Carbon tetrachloride etc. Measure purity of bitumen. → for good bitumen = 99.1% soluble (at least)
⑨ Water Absorption	→ $\neq 0.2\%$

गुणवत्ता प्रदर्श

Tile

Tile is a manufactured piece of fired clay, stone or concrete used covering walls, floor, roof & ornamental or architectural purpose.
Shape Mostly, square & rectangular.

Types of Tiles

[A] Based on Location

- ① Wall Tiles Laid on Wall Used Both inside & outside of building.
In Inside Bathroom & Kitchen Wall In outside Used for cladding.
- ② Floor Tiles Laid on floor
- ③ Roof Tiles Laid on Roof of a single story house.
- ④ Paver Tiles Laid on covering parking area, driveway, surrounding area of a building.

[B] Based on materials & Manufacturing process

- ① Ceramic Tiles Ingredients clay, silt, sand & traces other natural substances.

Aman

Commonly used Residential building in interior walls & floors.

Types of Ceramic Tiles

① Glazed Ceramic Tiles	② Unglazed Ceramic Tiles
→ Liquid glass coating over the top of tiles. → Appearance Infinite colour, finishes, texture	→ No coating → Appearance Natural, earthy
→ Water proof → Density Less	→ No water proof → Density High
→ Thickness Thick	→ Thickness Thicker
→ Durability Low → Slip	→ Durability More → Slip
→ Cost Expensive	resistance → cost cheaper

③ Porcelain Tiles similar to ceramic tiles. BUT Clay grain more finer fired in higher temperature than ceramic tiles. Also, Denser, Less porous, durable, resistant to moisture than ceramic tiles.

Used Both residential & commercial building.

④ Mosaic Tiles Made of Ceramic, glass, stone or metal

→ Decorative pieces used Bathroom, Kitchen, Swimming pool etc.

⑤ Clay Tiles Made by pressing & burning clay.

Used Low cost housing, roof of building.

Testing of Tiles

Test	Explanation
General quality test	→ Well burnt or not → Shape & Colour uniform or not → Cracks are present or not
Warping test	→ $\pm 2\%$ in sides → $\pm 5\%$ in diagonal
Water absorption test	→ $\pm 24\%$
Dimension test	→ Required dimension or not

Anam

गणेशजी / मोक्षजी प्रवेश

Aggregates

Aggregates are **inert materials** mixed with a binding material (cement, lime) in the preparation of mortar & concrete.

Types of Aggregates

A) Based on size

① Fine Aggregates	② Coarse Aggregates
→ small size finer materials in construction.	→ Larger size finer materials in construction.
→ pass 4.75 mm sieve. IS	→ pass 75 mm sieve.
→ Retain 0.075 mm sieve. (75 micron)	→ Retain 4.75 mm sieve
→ Example sand, stone screening, surkhi, fly ash etc.	→ Example gravels, pebbles, brick & stone chips, clinkers etc.
→ Function Voids between the coarse aggregate are filled up.	→ Function Acts as inert filler material for concrete

B) Based on shape

Types of Aggregates	Explanation
① Rounded Aggregates	→ Voids 32-33% → Good Workability.
	→ Strength More Bond Strength Less.
	→ Not suitable High strength concrete
② Irregular Aggregates	→ Voids generate 35-38% → Less Workability → So Water & Cement are more required for constant W/c ratio.
	→ Bond strength More than Rounded aggregates
	→ Not suitable High strength concrete.
③ Angular Aggregates	→ Voids 38-40% → Less Workability than Rounded aggregate → Bond Strength More
	→ Suitable High strength concrete.

Aman

C Based on moisture content :

Types of Aggregate	pores	Surface
① Very dry aggregate	No moisture	No moisture
② Dry aggregate	some moisture	No moisture
③ Saturated surface dry aggregate	Filled with water	Dry
④ Moist aggregate	Filled with water	Wet

D Other Aggregate

Types of Aggregate	Explanation
① All-in-aggregate	→ Which contain fine & coarse aggregate
② Flaky aggregate	→ Least dimension $< 0.6 \left(\frac{3}{5}\right)^{\text{th}}$ times it's mean dimension
③ Elongated aggregate	→ Least dimension > 1.8 or $\left(\frac{9}{5}\right)^{\text{th}}$ times it's mean dimension
④ Cyclopean aggregate	→ Size $> 75 \text{ mm}$.

Note size of aggregate for concrete = 20mm

mass concrete = 40 mm or more.

Flooring = 10 mm.

Quality of good Aggregate

- ① Strength → sufficient strength to resist stress.
- ② Durability → Resistance to weathering, environmental factor
- ③ Shape & size → Uniform, compacted, interlocked effectively
- ④ Water absorption → $< 10\%$.
- ⑤ Cleanliness → Free from organic matter, clay, etc.

Test of Aggregate

Types of Test	Explanation
① Impact Test	→ Apparatus Impact testing machine.
	→ Find Toughness.

Note Book

Date : 20 / /

Aman	
② Crushing test	→ Instrument crushing test machine. → Find strength.
③ Abrasion test	→ Instrument Los Angeles machine. → Find wear & tear.
④ Soundness test	→ Find durability.
⑤ Water absorption test	→ $< 10\%$.
⑥ Bitumen adhesion test	→ Find stripping value. → Stripping aggregate, यह bitumen अच्छा water-तिर आकर्षित हुआ।
⑦ Shape test	→ Determine by % of flaky & elongated particles contained in it & by its angularity.

कौशी प्रदेश

Timber

Timber is a wood that is used for the construction purpose.

→ Freshly felled timber consists of 100% moisture of dry weight & 50% moisture of total weight. (Amount of moisture = Amount of timber seasoning. The process of reduction of moisture from timber.

Method of seasoning → Good quality

- ① Natural Method → Air dried is done. → Time consuming (6-8 month) → Less efficient (Reduce moisture up to 12-15%) → Economical
- ② Artificial Method / Kiln Method → Controlled heat & humidity is used to reduce the moisture content. → Fast → Reduce moisture up to 0% → Costly
- ③ Chemical & Electrical seasoning.

Purpose of seasoning.

- Make fire resistance → Water proof → Make light, strong, stable
- prevents warping, cracking, shrinkage. → resistant to decay by fungi, termites (एगिरा) etc. → resistance to electricity.

Aman

Classification of Timber

A Based on Growth Mode


- ① Endogenous → Growth endward → Example Bamboo, Coconut, palm, Walnut (ओखर).
- ② Exogenous → Growth outward → Example sal, teak, deodar, shisham

Types of Exogenous

- | | |
|-------------|---|
| ① Conifers | → Pointed leaves (पुच्छे पत्त) Example Deodar, chir |
| ② Deciduous | → Flat leaves (चौड़ा पत्त) Example teak, shisham, oak |

B Based on Hardness

- ① Hard wood — sal, teak, shisham, oak etc.
- ② Soft wood — deodar, walnut, kail, fir, chir etc.



Internal structure of wood

- ① Pith Innermost part or core of tree. Also called Medulla
- ② Heart Wood Innermost annual ring. Also called Duramen. Responsible for strength, hardness. Colour darker
- ③ Sap wood Living part of timber. Colour Light → outermost annual ring. → Active & younger part. Function Transmits the sap from roots to branches.

Note Book


Date : 20 / /

Aman

- ④ Bark **Outermost skin** of tree. **Function** protects inner portion of tree from external injuries. **Inner bark** → **live bark**. **Outer bark** → **dead bark** → Inner bark covering cambium layer.
- ⑤ **Cambium layer** **Layer of wood** between bark & sap wood. → if cambium layer is exposed to atmosphere, tree dies.
- ⑥ **Annual Ring** **Ring formed in timber**. (Heartwood → Cambium layer) **Determine** Age of tree. → **Total no. of annual ring = Age of tree**.
- ⑦ **Medullary rays** → It **extends radially** from pith to cambium layer. **Function** Binds all annual ring. → Carries nutrients outward.

Defects of Timber

- ① **Foxiness** Timber turning into **yellowish or red** around pith. **Reason** → **over maturity**. → **poor ventilation**.
- ② **Knots** → **Root of the branch** → Annual ring perpendicular to stem.
- ③ **Rind galls** → **swollen part of timber** due to improper cutting.
- ④ **Bird eye** → **small, circular areas** on wood surface caused by indented **wood fibers**.
- ⑤ **Burl** → **uneven projection** on the body of the tree during its growth. **Reason** **suck & injury** in its young age. → Due to **hardening**.
- ⑥ **Druxiness** → Top surface of timber indicates **white spots**. **Reason** **Access of fungi**.
- ⑦ **Upsets** → **fibres injured** by crushing or compression.
- ⑧ **Rupture** → **caused due to injury** or impact.
- ⑨ **Twisted fibres** → **caused by wind** constantly turning the trunk of young tree in one direction.
- ⑩ **Checks & shakes** → **lengthwise separation** of wood is known as checks while **perpendicular to length** is called shakes.
- ⑪ **Wood Warping** → **deviation from flatness** **Reason** **Uneven drying**. **Result** of stress & shrinkage. **Types of Wood Warping**.



Aman

Types of shake

① Heart shake	② Star shake	③ Ring shake
		
→ Cracks in central part. Caused by over-maturity.	→ Cracks from bark. Caused by over heat of sun & frost.	→ Separation of annual ring. Caused by strong wind.

Diseases of Timber

Rot Rot is a types of diseases due to which life of wood reduces or becomes useless.

Types of Rot

- ① **Dry Rot** → Convert wood into fine powder. Reason Lack of Ventilation & absence of moisture. Agency Fungus (zarr). Remedy Well seasoned the timber & painting with Copper sulfate.
- ② **Wet Rot** → Convert wood into Grayish-brown powder. Reason Alternate wetting & drying & excess moisture. Agency Excessive Water. Remedy Well seasoned the timber & paints.

Termites or White ants → Insect (कीरा) है। → Damages to timber. Reason dampness. Agency Insect. Remedy Anti-termite.

preservation of Timber

- ① **Charring** → Burning of timber surface. for inserted inside ground. Protects from white ants, fungi.
- ② **Tarring** → Applying coat of tar. for door & window frame.
- ③ **Painting** → oil paint are suitable → prevents from moisture.
- ④ **Creosoting** → Prepared by distillation of tar. → Colour black or brown → Unpleasant (अशुभ) smell. → Apply Creosote oil on timber. for Wood piles, poles, railway-sleepers etc. Not used fire places.

Note Book

Date : 20 / /

Amu

⑤ Ascu process → Ascu is in powder form. → It is dissolve in water. & applied over timber.

⑥ Wolman salt → contain 25% sodium fluoride, 25% disodium hydrogen arsenate, 37.5% sodium chromate & 12.5% dinitrophenol

* Fire resistance of timber - The fire resistance of timber can be enhanced either by impregnating it with chemical like phosphate of ammonia, ammonium chloride, mixture of ammonium phosphate & ammonium sulphate, borax & boric acid, sodium arsenate, sodium tetra-borate or by designing wood to provide slow burning constituent.

PLY. Wood

It is combination of veneers. → Veneers are placed to each other by gluing. Veneers thin sheet of wood sliced from log. → Thickness = 0.4 - 6 mm.

Note : Density of timber = $\frac{1}{12}$ th of steel.

→ Strength of timber = $\frac{1}{10}$ th of steel.

→ Strength of timber increase with increase Medullary ring.

→ Timber is an organic material having cellular structure.

→ Defect due to imperfect seasoning = honey combing

→ Moisture content of timber formwork = > 15%

→ Used Timber formwork → 4-5 times steel formwork → upto 50 tim

→ Good timber sound = sonorous → Used for railway. Slipper = sal, kail

→ Board Thickness = < 5 cm & width = exceeds 12 cm

→ Strip Thickness = 5 cm & width = 10 cm

→ Thickness of five ply sheet = 6-9 mm

→ Thickness of lamin board = 12-25 mm.

Aman

Sawing Method

① Ordinary Method / Flat Method

→ Most shrinkage & warping.

② Tangential Method

→ Less wastages. → Most economical.

③ Radial Method

→ Maximum strength → Maximum wastages.

④ Quarter Method

Terms

① Log Timber obtained after removing all the branches.

② Batten piece of sawn timber Thickness $< 5\text{cm}$ & width $< 5\text{cm}$

③ Plank " " " " Thickness $< 5\text{cm}$ & width $> 5\text{cm}$

④ Board " " " " Thickness $< 5\text{cm}$ & width $\geq 12\text{cm}$

⑤ Strip " " " " Thickness $< 5\text{cm}$ & width $< 10\text{cm}$

⑥ Bouik " " " " Thickness $> 5\text{cm}$ & width $> 20\text{cm}$

पंजी प्रदेश

Metals & Alloys

Metal Metal is a solid material which is typically hard, shiny, malleable & ductile with good conductor of heat & electricity.

Types of Metals

→ They are magnetic!

① Ferrous Metals main constituent Iron Example Iron, steel

Widely used different engineering structure such as building frames, beams, columns, roof, bridges etc.

② Non-ferrous Metal main constituent Not iron. → They are

not magnetic. Example Aluminium, copper, Lead, zinc, Tin etc

Note Book

Date : 20 / /

Answer

Ore It is type of material used to extract metals.

Name of Ore	Iron content	Chemical Formula
① Magnetite (black iron ore)	70-75%	Fe_3O_4
② Hematite (Red iron ore)	70%	Fe_2O_3
③ Limonite (Brown iron ore)	60%	$2Fe_2O_3 \cdot 3H_2O$
④ Iron pyrite (Iron disulphide)	47%	FeS_2
⑤ Siderite	40%	$FeCO_3$

Types of Iron → Lowest quality
→ Remove impurities

A Pig Iron → first & basic form → Crude & impure iron.
→ Manufactured in blast furnace. → Carbon content = 3-4%.

Types of Pig Iron

① Bessemer Pig. Obtained from Hematite ore Free from sulphur, phosphorus & Copper. Used for make Mild steel.

② Foundry / Gray Pig Obtained from Furnace → sufficient fuel at high temperature and → Used for make Cast iron.

③ Forge / White pig → obtained from Furnace → sufficient fuel at low temperature and → Used for make Wrought iron.

④ Mottled pig. → Property between foundry & forge pig. Used for heavy Casting equipment.

B Cast Iron → Obtained by melting pig iron obtained from Cupola Furnace → Carbon content = 3% → More pure than pig iron.

→ Hard & brittle. → Used Structural work & Cast iron pipes.

C Wrought Iron → purest form of iron. → Carbon content = 0.15%
→ soft & easily welded. → produced by Removing impurities of cast iron. Used plate, rivets, sheet, pipe tube, railing, Window guards etc.

D Steel → Most suitable building material.

Unit Weight of steel = 7850 kg/m^3

Coefficient of thermal expansion = $11.5 \times 10^{-6} \text{ per } ^\circ\text{C}$.

→ Intermediate form between Cast iron & wrought iron.

Aman

Classification of steel

Types of steel	① Dead MS	② Mild	③ medium carbon	④ High carbon	Tool steel
Carbon content (%)	< 0.15	0.15 - 0.3	0.3 - 0.8	0.8 - 1.5	> 1

* Mild steel → Low carbon, ductile, malleable & more elastic than wrought iron. → Ultimate comp. strength = 800-1200 N/mm²

Tensile strength = 600-800 N/mm². → Rust quickly.

→ can be permanently magnetized Uses construction work.

nuts, bolts, plates, reinforcement bars, roof covering etc.

→ sp. gravity = 7.8 → Tough → soft → Easily forged

* Medium carbon steel → stronger & harder than mild steel. → Less ductile, tough, malleable. Used metal ropes, wires, garden tools, automobile components.

* High carbon steel → Hardest → Less ductile, tough & malleable. → Better resistance wear & tear, shocks & vibrations. → More difficult to forge & weld.

→ Ultimate comp. strength = 1350 N/mm² → Tensile strength = 1400-2000 N/mm². → Used To make chisels, hammers, drills, files, lathe tools, hacksaw, blades etc.

Alloys

An alloy is a combination of metals or other substance.

Name of Alloy	Elements	%
1. Brass	Copper + Zinc	60+40
2. Bronze	Copper + Tin	90+10
3. Invar	Steel + Nickel	64+36
4. Monel metal	Copper + Nickel	60+40
5. Stainless steel	Chromium + Nickel → 16% मन्दा धातु	18+8
6. Solder	Lead + Tin	1:2
7. German silver	Copper + Zinc + Nickel	
8. Brazing solder	Copper + Zinc + Tin	4:3:1

Note Chromium is added to make steel corrosion resistance.

Note Book

Date : 20 / /

Aman	
9. Gun metal	Also called Red brass considered both brass & bronze contains 85% copper + 5% tin + 5% zinc + 5% lead Used: produce pipes, valves etc.
10. Galvanising	→ depositing a fine film of zinc on steel/iron.
11. Electroplating	→ depositing a fine film of Nickel, chromium, cadmium, copper or zinc on surface of metal

Note : → 1% of cobalt in carbon steel to make magnet = 45%.

→ Vanadium steel is generally used for axle & springs.

→ Yield & tensile strength of low carbon steel may be improved by the addition of Vanadium.

→ Malleability: different shape by heating.

→ Ductility: Transferred into wire.

→ Minimum 40% of iron is available in blackband.

→ Red short iron cracks when bent due to presence of sulphur.

→ Brittleness of cold is due to excessive phosphorous.

Extra

Lime

Lime is basically calcium oxide (CaO). It is not found in nature in free state. It is obtained by burning limestone at 800°C . or calcination of limestone with chalk, kankar & other calcareous substance. → cementing material → It easy for working.

→ provides strength to the masonry.

→ Used → plastering interior surface of wall, preparing concrete for foundation, flooring of ordinary building, washing the rooms, stabilizing the soil & knotting of timber works before painting.

Note : → In Lime manufacturing, fuel not direct contact with lime.

Flare kiln & direct contact = flame kiln → sand mixed with lime mortar to prevent shrinkage & cracking.

Amam

Types of Lime

(A) Based on source

- ① Stone Lime From Limestone Uses Mortar, flooring
- ② Kankar Lime From Kankar Uses Mortar (substructure)
- ③ Shell Lime From shells of sea animals Uses Lime punning, White wash & colour wash.

(B) Based on purity → obtained by burning limestone

① Fat, rich, pure, high calcium & white lime

- Impurity $< 5\%$ → Volume - 2-3 times after slaking
- Uses plaster, white washing etc. → Colour milky white
- Sound produce Hissing → Contains 95% limestone & 5% other materials. → Soluble in water. → Setting & hardening action are slow. → slaking complete = 3-4 hrs

② Hydraulic Lime / Water Lime

- Impurity 5-30% → Volume 2-3 times after slaking.
- Uses for making mortar for heavy masonry works, lime concrete, work under water & foundation. → Colour Grayish white. → Sound produce Not hissing → Slaking complete 24-48 hrs. obtained by burning kankar.

→ Initial setting time = 120 min. → Contain 30% of clay.

Types of Hydraulic Lime

① Feebly Hydraulic Lime Silica & alumina $< 10\%$, Slaking time = 5-15 min → setting time = 21 days.

② Moderately Hydraulic Lime Silica & alumina = 10-20%.

→ slaking time = 1-2 hrs → setting time = 7 days.

③ Eminently Hydraulic Lime → Silica & alumina = 20-30%.

→ slaking time = 2-5 hrs → setting time = 2-48 hrs.

③ Poor or Lean Lime

→ Impurity $> 30\%$ → Uses poor mortar & plaster

→ Also called Meager lime → Colour Muddy white

Note Book

Date : 20 / /

Answer

→ slaking Very slowly → Hardens Very slowly. NOT SET

Under Water:

Note: for slaking 10 kg of CaO = 3.2 kg Water

Based on purpose

Theoretical

① Class A (Eminently hydraulic lime) → CaO 60-70% → Clay 20-30%
Setting time = 2-48 hrs. Uses Mortar & concrete.

② Class B (semi hydraulic lime) → CaO 70% → Clay 15% →
Setting time = 7 days → Uses mortar, flooring & concrete.

③ Class C (fat lime) → CaO 93% → Clay 5% → Volume = 2-3 times
after slaking. → Uses plaster & white washing.

④ Class D (magnesium lime) → CaO & MgO 85% Uses plaster &

⑤ Class E (Kankar lime) → CaO 20% → MgO 5% → White Wash
mortar, plaster & white washing.

Note: Normal curing period for lime mortar = 7 days.

Terminology

① Coarse stuff → material of rough or uneven texture.

② Hydrated lime → dry powder → Obtained by Treatment of
quick lime with water → Also called slaked lime.

③ Quick lime → Obtained by calcination of pure limestone.
Also called fat, rich or pure lime.

④ Milk lime → Thin pourable solution of slaked lime with water.

⑤ Lump lime → Quick lime as it comes from kiln.

⑥ Calcination → process of heating lime stone in contact with air.

⑦ Slaking → process of adding water to quick lime to form calcium
hydroxide.

⑧ Lime putty → obtained by slaking or mixing quicklime with water.

Test on Lime

① Visual inspection → Examined for its colour & lumps.

② Hydraulic acid test → Find carbonate content of lime.

③ Soundness test → Find quality of lime.

④ Workability test → know the workmanship.

⑤ Ball test → Find expansion & disintegration of ball of lime.

⑥ Impurity test → < 10% good → 10-20% fair → > 20% poor